



PRODUCT

DATA SHEET

Flux Cored Stainless Steel Electrodes (Gas Shielded)

Weld Process: Gas Metal Arc

Alloy: E310T-1 Class: E310TX-X

Conforms to Certification: AWS A5.22 ASME SFA 5.22

Alloy: DM310T-1

AWS Chemical Composition Requirements

C = 0.20 max	S = 0.03 max
Mn = 1.0 – 2.5	Cr = 25.0 – 28.0
Si = 1.0 max	Ni = 20.0 – 22.5
P = 0.03 max	Mo = 0.75 max
Cu = 0.75 max	

Deposited Chemical Composition % (Typical)

C = 0.14	Mn = 1.75	Si = 0.67
P = 0.002	S = 0.002	Cr = 27.0
Ni = 21.25	Mo = 0.38	

Deposited All Weld Metal Properties %

As-Welded

Tensile Strength	85,000psi
Elongation	34%

Deposited Charpy-V-Notch Impact Properties %

Not applicable

Application

The nominal composition of this weld metal is 26.5% chromium and 21% nickel. These electrodes are most often used to weld base metals of similar compositions.

Suggested Welding Parameters

Diameter .035

	<u>Optimum Parameters</u>			<u>Operating Range</u>	
	Wire Feed Speed	Amps	Volts	Amps	Volts
Flat	365"/ minute	130-140	24-25	100-170	21-26
Horizontal	365"/ minute	130-140	24-25	100-170	21-26
Vertical-Up	310"/ minute	110-120	22-23	110-120	21-23
Overhead	320"/ minute	120-130	23-24	120-130	22-24

Diameter .045

	<u>Optimum Parameters</u>			<u>Operating Range</u>	
	Wire Feed Speed	Amps	Volts	Amps	Volts
Flat	450"/ minute	180-200	25-27	135-250	24-32
Horizontal	450"/ minute	180-200	25-27	135-250	24-32
Vertical-Up	325"/ minute	150-170	24-26	135-200	24-26
Overhead	425"/ minute	175-195	25-27	155-200	25-28

Diameter 1/16

	<u>Optimum Parameters</u>			<u>Operating Range</u>	
	Wire Feed Speed	Amps	Volts	Amps	Volts
Flat	264"/ minute	220-240	25-27	170-300	24-31
Horizontal	235"/ minute	200-220	25-27	170-270	24-29
Vertical-Up	220"/ minute	190-210	25-26	170-230	24-27
Overhead	235"/ minute	200-220	25-26	170-270	24-29

For best results, set the wire feed speed and adjust the voltage for smoothest operation. Electrode extension range is from 1/2" to 1," with an optimum range of 5/8" to 3/4." Weld using reverse polarity DC(+).

Shielding Gas

75% argon / 25% CO₂ (or nearest equivalent) shielding gas; however, straight CO₂ may also be used. The 75/25 mixture will produce a smoother arc with virtually no spatter and slightly higher yield and tensile strengths than CO₂. The mechanical properties and deposit analyses will meet AWS A5.22 specifications with either gas.



PRODUCT DATA SHEET