DURA MAX E347-16 - DM347-16 FLUX COATED STAINLESS STEEL ELECTRODE

Classification: AWS A5.4 / ASME SFA 5.4

Typical Application

A low carbon, 19Cr-10Ni-Cb stainless steel electrode depositing stabilized weld metal.
Weld metal offers excellent resistance to intergranular corrosion. Electrode gives smooth arc, easy slag detachability and is almost spatter free with fine finish weld deposit.

Characteristics on Usage

1) Ideally suitable for welding stainless steel conforming to AISI 304, 304L, 321, 347.
2) And their equivalents used in fertilizer, petrochemical, chemical and pharmaceutical industries.

Flux Color: White - Grey

All Weld Chemical Composition (%)

C	Cr	Ni	Mo	Mn	Si	P	S	Cu	Nb (Cb) + Ta
0.08 max	18.0-21.0	9.0-21.0	0.75 max	0.5-2.5	1.00 max	0.04 max	0.03 max	0.75 max	8 x C min to 1.00 max

Typical Mechanical Properties

Tensile Strength	Yield Strength	Elongation (1=4d)	Impact Energy	Ferrite WRC
590 N/mm2	420 N/mm2	42%	+20°C : 60-80 J	4 - 10

Microstructure: Austenite with 4 - 10% ferrite. Typical ferrite number is 6.

Sizes available and recommended currents (DC +) or (AC)

Amps for Positions / Diameters		**5/64**	**3/32**	**1/8**	**5/32**	**3/16**
Amp	F/H-Fillet	35 ~ 55	50 ~ 85	80 ~ 120	100 ~ 150	140 ~ 200
Amp	V-up/OH	30 ~ 50	45 ~ 85	70 ~ 110	90 ~ 135	----

RE-DRY CONDITION: Re-Dry the electrode at 250°C for 1 hrs before use.

POLARITY: DCEP or AC
DCEP = DC, Electrode Positive (reverse polarity) has the most weld penetration.
AC: medium weld penetration (can be more spatter)
USE LESS AMPS ON THIN METAL; MORE AMPS ON THICK METALS
WELDING POSITIONS: Flat, Horizontal, Vertical-up and Overhead positions

DURAMAX Brand **103 Queens Drive** **King of Prussia, PA 19406**
Phone: (484) 808-4200 **Toll free: (800) 692-5930** **Fax: (610) 265-1012**

The above information is to be use as a guideline and is taken directly from the manufacturers Technical Data Sheet. If additional information is needed please contact us at 1-800-692-5930