

PRODUCT

DATA SHEET

Stainless Steel Bare Wire

Weld Process: Used for Mig, Tig, & Submerged Arc

Alloy: 409Nb Class: ER409Nb formally ER409Cb

Conforms to Certification: AWS A5.9 / ASME SFA 5.9

Alloy: DM409NB



PRODUCT

DATA SHEET

AWS Chemical Composition

 $\begin{array}{lll} C = 0.08 \ max & Si = 1.00 \ max \\ Cr = 10.5 - 13.5 & P = 0.04 \ max \\ Ni = 0.60 \ max & S = 0.03 \ max \\ Mo = 0.50 \ max & Cu = 0.75 \ max \end{array}$

Mn = 0.80 max $Nb = 10 \times C \text{ (min)} - 0.75 \text{ (max)}$

Deposited Chemical Composition % (Typical)

C = 0.05		Mo = 0.30	
0.016			
Cr = 11.5	Mn = 0.62	S = 0.018	
Ni = 0.35	Si = 0.48	Cu = 0.16	
Nb = 0.50			

Deposited All Weld Metal Properties

Data is typical for ER409CB weld metal deposited by mig using argon +2% oxygen and tig using 100% argon as the shielding gas. Data on sub-arc is dependent on the type of flux used.

Mechanical Properties R.T.

Yield Strength	50,500psi
Tensile Strength	67,000psi
Elongation	26%

Application

ER409Nb is a ferritic stainless steel welding wire which is used to weld Type 409 and 409Ti base materials. Addition of columbium leads to a preferential reaction with carbon, saving chromium from forming carbides. This improves corrosion resistance, increases strength at high temperatures.

Recommended Welding Parameters

<u>GMAW</u>	"Mig Pro	ocess"	Reve	ersed Polarity	
Wire <u>Diameter</u>	Wire Feed	Amps	Volts	Shielding Gas	Gas CFH
Short Arc	Welding				
.030 .035	13-26 13-26	40-120 60-140	16-20 16-22	Argon+2% O ₂ Argon+2% O ₂	25 25
Spray Arc	Welding				
.035 .045 1/16	20-39 16-30 10-16	140-220 160-260 230-350	24-29 25-30 27-31	Argon+2% O ₂ Argon+2% O ₂ Argon+2% O ₂	38 38 38

GTAW "Tig Process"

Wire <u>Diameter</u>	Amps DCEN	Voltage	Gases
.035	60-90	12-15	Argon 100%
.045	80-110	13-16	Argon 100%
1/16	90-130	14-16	Argon 100%
3/32	120-175	15-20	Argon 100%

Note: Parameters for tig welding are dependent upon plate thickness and welding position.

Other shielding Gases may be used for Mig and Tig welding. Shielding gases are chosen taking Quality, Cost, and Operability into consideration

Submerged Arc Welding

Reverse Polarity is suggested

Wire Diameter	<u>Amps</u>	<u>Volts</u>	
3/32	250-450	28-32	
1/8	300-500	29-34	
5/32	400-600	30-35	
3/16	500-700	30-35	

Both Agglomerated and fused fluxes can be used for submerged arc welding. Note: The chemical composition of the flux mainly affects the chemistry of the weld metal and consequently its corrosion resistance and Mechanical properties.